

Rock PEC - Geocomposites

Technical Data

TenCate Polyfelt Rock PEC biaxial geocomposites are engineered materials suitable for subgrade stabilisation and base reinforcement applications. They are composed of high modulus polyester fibres, attached to a continuous filament nonwoven geotextile backing.



TenCate Polyfelt Rock PEC

Properties <small>[Standard]</small>	Unit	PEC 35/35	PEC 55/50	PEC 75/75	PEC 95/95	
Mechanical Properties						
Tensile strength <small>[EN ISO 10319]</small>	MD	kN/m	37	58	79	100
	min	kN/m	35	55	75	95
	CD	kN/m	37	53	79	100
	min	kN/m	35	50	75	95
Elongation at nominal strength <small>[EN ISO 10319]</small>	MD	%	10	10	10	10
	CD	%	10	10	10	10
Tensile strength at 2% 3% 5% <small>[EN ISO 10319]</small>	MD & CD	kN/m	7.5	11.5	16	20
	MD & CD	kN/m	10	16	22	27
	MD & CD	kN/m	17	22	37	46
Hydraulic Properties						
Water permeability normal to the plane <small>[EN ISO 11058 - Δh = 50 mm]</small>		l/m ² s (mm/s)	55	55	55	55
Water flow capacity in the plane <small>[EN ISO 12958]</small>	20 kPa	10 ⁻⁷ m ² /s	20	20	20	20
Characteristic opening size O ₉₀ <small>[EN ISO 12956]</small>		μm	95	95	95	95
Forms of Supply						
Roll width		m	5.3	5.3	5.3	5.3
Roll length		m	100	100	100	100
Roll weight		kg	201	222	259	296

MD = machine direction / CD = cross direction min: These values are given within the 95% confidence level. Other forms of supply as well as grades, adjusted to the requirements of the project, are available on request.

For information concerning long term design strength, friction behaviour or other product properties please contact Ten Cate Geosynthetics.

The values given are average values obtained in our laboratories and in accredited testing institutes. The information given in this datasheet is to the best of our knowledge true and correct. However new research results and practical experience can make revisions necessary. The right is reserved to make changes without notice at any time. No guarantee or liability can be drawn from the information mentioned herein.

TENCATE GEOSYNTHETICS AUSTRIA GMBH

Schachermayerstrasse 18
A-4021 Linz, Austria

Tel. +43 732 6983 0, Fax +43 732 6983 5353
service.at@tencate.com, www.tencate.com

BeNeLux Tel. +31 546 544 811
Czech Republic Tel. +420 2 2425 1843
France / Africa Tel. +33 1 34 23 53 63
Germany Tel. +49 6074 3751 50
Italy / Greece / Turkey Tel. +39 0362 34 58 11
Near Middle East Tel. +44 2920 562 566
Poland Tel. +48 12 268 8375

service.nl@tencate.com
service.cz@tencate.com
service.fr@tencate.com
service.de@tencate.com
service.it@tencate.com
service.nme@tencate.com
service.pl@tencate.com

Romania
Russia / CIS
Scandinavia / Baltics
Spain / Portugal / LAM
Switzerland
UK / Ireland

Tel. +40 21 322 06 08
Tel. +7 495 739 12 60
Tel. +45 4485 7474
Tel. +34 91 650 6461
Tel. +41 44 318 6590
Tel. +44 1952 588 066

service.ro@tencate.com
service.ru@tencate.com
service.dk@tencate.com
service.es@tencate.com
service.ch@tencate.com
service.uk@tencate.com

