

MARKET SEGMENT : **WATER MANAGEMENT / MUSHROOM**
PRODUCT GROUP : **NICOLON® WATER STORAGE / COVERS**

PRODUCT : **NICOLON® C881/395 green-grey**

CONSTRUCTION	Unit		Standard
Basic material fabric		HDPE	
Basic material coating		LDPE	
Colour		green-grey	
Weight	gr/m ²	395	EN 965
Thickness	micron	600	EN 964-1

MECHANICAL PROPERTIES

Machine direction:

Nominal tensile strength	KN / m	26	EN ISO 527-4
Elongation at			
Nominal tensile strength	%	28	EN ISO 527-4
Tear resistance MD	N	300	DIN 53363

Cross direction:

Nominal tensile strength	kN / m	22	EN ISO 527-4
Elongation at			
Nominal tensile strength	%	30	EN ISO 527-4
Tear resistance CD	N	300	DIN 53353
CBR	kN	3,0	EN ISO 12236

Dynamic perforation	mm	14	EN-ISO13433
---------------------	----	----	-------------

Water tightness air pressure	WD 5/Bar	2	TCG-NL19
------------------------------	----------	---	----------

STANDARD ROLL AND PANEL SIZES

Roll length	m	500
Roll width	m	2.05
Maximum dimension panels	m ²	4000
Maximum width panels	m	50
Maximum weight panels	kg	1200

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.